UNISILKON L 641 Special grease for drinking water, beverage and heating valves



Description

UNISILKON L 641 is a special lubricating grease based on silicone oil and PTFE for valves and other elements in the heating, beverage and sanitary sector.

UNISILKON L 641 offers good penetration ability in small lubrication gaps and lube points of difficult access.

As its viscosity is rather independent from service temperatures, UNISILKON L 641 allows constant actuating forces within the whole cold/hot water range of single-lever mixer taps. The grease is compatible with most substances in the foodprocessing and beverage industries like beer, milk, juices, liquors, acid and alkaline disinfectants. UNISILKON L 641 is not compatible with most organic solvents as well as acid and alkaline solutions.

Application

UNISILKON L 641 is used as sealing and assembly aid for seals and packings in contact with hot and cold water or steam, e.g.: <u>domestic</u> <u>installations</u> - ball valves; <u>singlelever mixers</u> – piston cartouches, ceramic discs; <u>mixer taps with two</u> <u>handles</u> – swivel spouts, shower switches, shower heads; <u>thermostatic mixer taps</u> – thermo regulators and elements; <u>heating</u> – thermostatic valves, tap cocks, pressfit seals; <u>Water hydraulics</u> – sealing grease for radial shaft seals.

Application notes

data sheet.

UNISILKON L 641 is neutral towards metals, thermoplastics (e.g. ABS, PC) and elastomers (e.g. NBR, EPDM). Owing to the many different elastomer and plastic compositions their compatibility should be checked prior to series applications. UNISILKON L 641 can be applied by means of spatula, brush, usual metering devices or the tampon printing method. Please observe the material safety UNISILKON L 641

- Excellent wetting power
- Operational smoothness due to a good viscositytemperature behavior
- Excellent resistance to hot and cold water, steam
- High thermal stability
- Good sealing effect
- Neutral towards metals, elastomers and plastics
- Certified acc. to DVGW-KTW, WRC, USDA H1, AS 4020, NSF 51 and NSF 61

Minimum shelf life

The minimum shelf life is approx. 36 months if the product is stored in its unopened original container in a dry, frost-free place.

Pack sizes

500 g can 30 kg bucket

UNISILKON L 641 Special grease for drinking water, beverage and heating valves

Product data

Base oil	silicone oil
Thickener	PTFE
Service temperature range [°C]*	-40 to 160
Color	white
Texture	homogeneous, long-fibred
Density at 20°C, [g/cm³]	1.25
Worked penetration, DIN ISO 2137, at 25°C [0.1mm], approx.	300-320
Klüber viscosity class**	ES
Drop point, DIN ISO 2176 [°C]	>230
Water resistance, DIN 51807 part 1, 3h/90°C, rating	≤1-90

* Service temperatures are guide values which depend on the lubricant's composition, the intended use and the application method. Lubricants change their consistency, apparent dynamic viscosity or viscosity depending on the mechano-dynamical loads, time, pressure and temperature. These changes in product characteristics may affect the function of a component.

** Klüber viscosity grades: EL = extra light lubricating grease; L = light lubricating grease; M = medium lubricating grease; S = heavy lubricating grease; ES = extra heavy lubricating grease

The data in this product information is based on our general experience and knowledge at the time of printing and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary tests with the selected product. We recommend contacting our Technical Consulting Staff to discuss your specific application. If required and possible we will be pleased to provide a sample for testing. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this product information at any time without notice.



Klüber Lubrication, a member of the Freudenberg group

Publisher and Copyright: Klüber Lubrication München KG Reprints, total or in part, are permitted if source is indicated and voucher copy is forwarded.

Klüber Lubrication München KG Geisenhausenerstraße 7, 81379 München, Deutschland ☎ +49 89 7876-0, Telefax +49 89 7876-333, www.klueber.com